



FABBRICA TERRE COLORANTI – OSSIDI – COLORI PER RESTAURO – COLORI PREDISPERSI

37129 VERONA – Via Cantarane, 16 – Tel. 045 8007126- Fax. 045 8044204

e-mail: dolcicolor@tin.it

SCHEDA TECNICA

OSSIDO DI FERRO ARANCIO C 960

TYPE	FEOX ARANCIO C960	
Fe ₂ O ₃	%	≥ 88
Oil absorption	g/100 g	25 - 35
Residue on 325 mesh	%	≤ 0.3
Water soluble matter	%	≤ 0.3
Matter volatile at 105°C	%	≤ 1.0
pH value		3 - 7
Tinting strenght	%	95 - 105

Data : 4 agosto 2025